



Standard Specification for Chrome Yellow and Chrome Orange Pigments¹

This standard is issued under the fixed designation D 211; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers six types of commercially pure lead chromate pigments as follows:

- Type I—Primrose Chrome Yellow,
- Type II—Lemon Chrome Yellow,
- Type III—Medium Chrome Yellow,
- Type IV—Light Chrome Orange,
- Type V—Dark Chrome Orange, and
- Type VI—Chrome Yellow for Green.

1.2 The following hazard caveat applies to the test method portion of this specification only. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 126 Test Methods for Analysis of Yellow, Orange, and Green Pigments Containing Lead Chromate and Chromium Oxide Green²
- D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints²
- D 235 Specification for Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvents)³
- D 387 Test Method for Color and Strength of Chromatic Pigments with a Mechanical Muller⁴
- D 523 Test Method for Specular Gloss⁴
- D 562 Test Method for Consistency of Paints Measuring Krebs Units (KU) Viscosity Using a Stormer-Type Viscometer⁴
- D 600 Specification for Liquid Paint Driers³
- D 822 Practice for Filtered Open-Flame Carbon-Arc Exposures of Paint and Related Coatings⁴
- D 1210 Test Method for Fineness of Dispersion of Pigment-Vehicle Systems by Hegman-Type Gage⁴

E 97 Test Method for Directional Reflectance Factor, 45-deg 0-deg, of Opaque Specimens for Broad-Band Filter Reflectometry⁵

2.2 Federal Specification:

TT-R-266 Resin, Alkyd; Solutions⁶

3. Composition and Properties

3.1 The pigments shall be chemical precipitates consisting of normal or basic lead chromates, or mixtures of these, with or without admixtures of other insoluble compounds of lead or other materials used in manufacture to control certain properties. The pigments shall conform to the requirements for composition as prescribed in Table 1.

3.2 The mass color and character of the tint formed by mixture with a white pigment shall be the same as, and the strength shall be within mutually agreed upon limits of a standard acceptable to both the purchaser and the seller.

3.3 When mutually agreed upon between the purchaser and the seller as being essential to the end use of the pigment, resistance to loss of gloss, chalking, and color change shall be tested as specified in 5.1.4. The exposed panel shall show no chalking, a loss of not more than 30 % of the original gloss, and a color change no greater than the lightness difference. ΔL , shown for each pigment type in Table 2.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples for each 10 000 lb (4450 kg), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately, or samples from the same production unit may be blended in equal quantities to form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the following test methods. Test procedures not covered by ASTM

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Sept. 8, 1967. Originally published as D 211 – 25 T. Last previous edition D 211 – 63 T.

² Annual Book of ASTM Standards, Vol 06.03.

³ Annual Book of ASTM Standards, Vol 06.04.

⁴ Annual Book of ASTM Standards, Vol 06.01.

⁵ Discontinued; see 1992 Annual Book of ASTM Standards, Vol 06.01.

⁶ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098

TABLE 1 Requirements for Composition

| | Type I | Type II | Type III | Type IV | Type V | Type VI |
|-----------------------------------------------------------------------------|--------|---------|----------|---------|--------|---------|
| Lead chromate (PbCrO ₄), min % | 50 | 65 | 87 | 55 | 55 | 75 |
| Total matter soluble in water, max % | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 |
| Total of all substances other than insoluble compounds of lead, max % | 8.0 | 10.0 | 10.0 | 10.0 | 3.0 | 10.0 |
| Moisture and other volatile matter, max % | 1.5 | 1.5 | 1.5 | 1.5 | 1.5 | 1.5 |
| Coarse particles (total residue retained on a 45-μm (No. 325) sieve), max % | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 |
| Organic colors and lakes | none | none | none | none | none | none |

TABLE 2 Permissible Lightness Difference (ΔL)

| Type | Pigment | ΔL |
|------|-------------------------|----|
| I | Primrose chrome yellow | 35 |
| II | Lemon chrome yellow | 8 |
| III | Medium chrome yellow | 6 |
| IV | Light chrome orange | 3 |
| V | Dark chrome orange | 3 |
| VI | Chrome yellow for green | 6 |

methods shall be mutually agreed upon between the purchaser and the seller.

5.1.1 *Chemical Analysis of Dry Pigment*—Test Methods D 126. The lead chromate analysis should be conducted in accordance with 11.1 of Test Methods D 126; the procedure outlined in 11.2 is not applicable.

5.1.2 *Coarse Particles*—Test Methods D 185.

5.1.3 *Mass Color and Tinting Strength*—Test Method D 387.

5.1.4 *Resistance to Loss of Gloss, Chalking, and Color Change*:

5.1.4.1 A test enamel shall be prepared consisting of ingredients conforming to the applicable specifications in the following proportions:

| Ingredient | Weight Percent |
|----------------------------------------------|----------------|
| Pigment under test | 30 to 34 |
| Alkyd resin vehicle solids, min ^A | 28 |
| Total solids, min | 60 |
| Mineral spirits | B, C |
| Driers | D, E |

^A An alkyd resin solution conforming to Type III of Federal Specification TT-R-266 is suggested.

^B See Specification D 235.

^C As required to give a Stormer consistency of 100 to 150 g at 200 r/min as prescribed in Test Method D 562.

^D See Class B in Specification D 600.

^E As required to obtain set-to-touch in 2 h and dry-hard in 8 h.

5.1.4.2 The enamel shall have a fineness of grind, as prescribed in Test Method D 1210, of 1.5 mils or less. Apply the enamel to duplicate flat metal panels by spray or applicator to complete hiding and allow to dry 72 h. Measure the gloss at 60° in accordance with Test Method D 523. Measure the directional reflectance of the coating in accordance with Test Method E 97. Subject the coated panels for 168 h to accelerated weathering under the conditions prescribed in Practice D 822. Examine the exposed coating for chalking. Wash the exposed panel under running water with a thoroughly degreased lamb's wool pad to remove scum or dirt. Wipe off water with clean cheesecloth and dry the panel for 2 h. Calculate the loss of gloss from gloss measurements made before and after exposure. After exposure, determine the directional reflectance for each panel as described in Test Method E 97. Calculate the color change or lightness-difference estimate (ΔL) as follows:

$$\Delta L = K(Y_2^{1/2} - Y_1^{1/2}) \quad (1)$$

where:

Y_1 = luminous directional reflectance of the panel measured before exposure,

Y_2 = reflectance measured after exposure, and

K = 100 when the reflectances are expressed as decimal fractions or 10 if reflectances are expressed in percent.

The color change for the coating shall be the average obtained for the two panels.⁷

6. Keywords

6.1 chrome orange; chrome yellow; lead chromate; orange pigments; pigments; yellow pigments

⁷ The method of determining the lightness-difference estimate is described in detail in example 4, "Photoelectric Tristimulus Colorimetry with Three Filters," Circular C429, Nat. Bureau Standards.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).