

Standard Specification for Vulcanized Fibre Sheets, Rods, and Tubes Used for Electrical Insulation¹

This standard is issued under the fixed designation D 710; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers vulcanized fibre (Note 1) sheets, round rods, and round tubes of such grades suitable for use as electrical insulation.

Note 1—The variant spelling "fibre" has been approved by Committee D09 for use in this standard.

1.2 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:

- D 495 Test Method for High-Voltage, Low-Current, Dry Arc Resistance of Solid Electrical Insulation²
- D 619 Test Methods for Vulcanized Fibre Used for Electrical Insulation²
- D 696 Test Method for Coefficient of Linear Thermal Expansion of Plastics Between 30° C and 30° C With a Vitreous Silica Dilatometer³
- D 952 Test Method for Bond or Cohesive Strength of Sheet Plastics and Electrical Insulating Materials³
- D 3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials⁴

2.2 Other Documents:⁵

IEEE Publication No. 1, "General Principles for Temperature Limits in the Rating of Electrical Equipment."

3. Terminology

3.1 *Definitions*:

3.1.1 *vulcanized fibre*, *n*—a material made from chemically gelatinized cellulosic paper or board using zinc chloride as the gelatinizing agent.

² Annual Book of ASTM Standards, Vol 10.01.

⁴ Annual Book of ASTM Standards, Vol 10.02.

3.1.1.1 *Discussion*—The zinc chloride is subsequently removed by leaching. The resulting product, after being dried and finished by calendering, is a material of partially regenerated cellulose in which the fibrous structure is retained in varying degrees depending on the grade of paper used and on the processing conditions. Material up to about 25 mm in thickness is produced by bonding multiple layers of paper (or board) after chemical treatment. Vulcanized fibre does not contain vulcanized rubber or sulfur as the name might imply. Thin vulcanized fibre has sometimes been termed "fish paper."

4. Grades

4.1 Three grades of vulcanized fibre are covered, as follows:

4.1.1 *Bone Grade*—This grade is characterized by the greater hardness and stiffness associated with higher density. It machines more smoothly and with less tendency to separate the plies in difficult machining operations than the other grades. It is made in thickness of $\frac{1}{32}$ to $\frac{1}{4}$ in. (0.79 to 6.35 mm).

4.1.2 *Commercial Grade*—This grade is considered as the general-purpose grade and is sometimes referred to as mechanical and electrical grade. It possesses good physical and electrical properties and can be fabricated satisfactorily by punching, turning, and forming operations. It is made in thicknesses from 0.010 to ¹/₄ in. (0.25 to 6.35 mm).

4.1.3 *Electrical Insulation Grade*—This grade is intended primarily for electrical applications and others involving difficult bending or forming operations. It is made in thicknesses from 0.004 to $\frac{1}{8}$ in. (0.10 to 3.2 mm). Thin material of this grade is sometimes referred to as "fish paper."

4.2 The three grades of fibre are available in laminated sheet form in greater thicknesses than those listed in 4.1.1 to 4.1.3. Laminated (or built-up) fibre is composed of a number of plies bonded together with a suitable adhesive. It retains all the basic properties of solid fibre, including high arc resistance on edges and faces, and in addition has better dimensional stability and less warpage. Laminated fibre is usually furnished when the thickness is over ¹/₄ in. (6.35 mm), and may be furnished in thicknesses down to ¹/₈ in. (3.2 mm). Thicknesses up to 4 in. (102 mm) are commercially available.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

Current edition approved Sept. 10, 1997. Published November 1997. Originally published as D 710 - 43 T. Last previous edition D 710 - 96.

³ Annual Book of ASTM Standards, Vol 08.01.

⁵ Available from The Institute of Electrical and Electronics Engineers, Inc., 445

Hoes Ln., P.O. Box 1331, Piscataway, NJ 08854-1331.

4.3 Thin sheet material, up to $\frac{1}{16}$ in. thick is available in a lower density uncalendered condition which may not meet the requirements of this specification.

5. Forms and Colors

5.1 Vulcanized fibre is available in the forms and colors listed in Table 1.

6. Chemical Composition

6.1 The material shall conform to the requirements for chemical composition prescribed in Table 2.

7. Detail Requirements

7.1 Sheets-Sheet material, calendered only, unless otherwise specified, shall conform to the requirements as to physical and electrical properties prescribed in Tables 3-9.

7.1.1 Bond Strength (Laminated Sheets Only)-Tested in accordance with Test Method D 952 shall conform to the following requirements:

Thicknesses	Psi, (MPa) min
All	800 (5.5)

7.2 Round Rods-Round rods shall conform to the requirements as to physical properties prescribed in Tables 10 and 11, and Table 12.

7.3 Round Tubes-Round tubes shall conform to the requirements as to physical and electrical properties prescribed in Tables 13 and 14. Density of tubing shall conform to the requirements prescribed in Table 6 for the respective grade and thickness.

8. Sheet Sizes and Permissible Variations

8.1 Sheets shall be furnished in the manufacturer's standard sheet sizes.

NOTE 2-The range of manufacturer's standard sizes for the various grades and thicknesses are shown in Table 15.

8.2 When sheets and rolls are trimmed to a specified width, the maximum permissible variation in width is $\pm \frac{1}{2}$ in. (± 12.7 mm).

8.3 When sheets are trimmed to a specified length, the maximum permissible variation in length is $\pm \frac{1}{2}$ in.

8.4 The maximum permissible variations in widths of strips cut from sheets by the indicated operations are as prescribed in Table 16.

8.5 The maximum permissible variation in thickness of full sheets is as prescribed in Table 17.

8.6 The maximum permissible variations in thickness of sheets cut in halves, thirds, or quarters are as shown in Table 17.

TABLE 1	Forms	and	Colors	Available
---------	-------	-----	--------	-----------

Grades	Forms ^A	Colors ^B
Bone	sheets and rods, tubes	gray gray, black, red
Commercial	sheets and rods	gray, black, red
Electrical Insulation	sheets	gray

^A Sheets and rods are available in both single-laver and laminated form. Thin sheets are available in both rolls and flat sheets in thicknesses up to 1/16 in. (1.6 mm).

^B In any of these standard colors, considerable variation of shade may be expected.

TABLE 2 Chemical Requirements

Grade	Color	Zinc Chloride, max, %	Ash max, %	Silica Content, max, %
All	gray, black	0.1	1.5	0.3
	red	0.1	7	0.3

TABLE 3 Flexural Strength Requirement for Sheets, min, psi (MPa)

(2)					
Neminal Thielmann in	Bone	Grade	Commercial Grade		
(mm)	Length-	Cross-	Length-	Cross-	
(11111)	wise	wise	wise	wise	
1/16(1.59) up to 1/8	16 000	14 000	15 000 ^A	13 000 ^A	
(3.18), incl	(110)	(97)	(103)	(90)	
Over 1/8(3.18) to 1/2	15 000	13 000	14 000	12 000	
(12.7), incl	(103)	(90)	(97)	(83)	
Over 1/2(12.7) to 1			13 000	11 000	
(25.4), incl			(90)	(76)	

^A These two values also apply to Electrical Insulation Grade.

TABLE 4 Water Absorption and Dielectric Strength Requirements for Sheets

Grade	Nominal Thickness,	Water At ma	osorption, ^{<i>A</i>} x, %	Dielectric Strength, ^B
	III. (IIIII)	2 h	24 h	V/mil (kV/mm)
Bone	1/32(0.79)	55	63	175 (6.9)
	1/16(1.59)	30	55	175 (6.9)
	1⁄8(3.18)	20	48	150 (5.9)
	3⁄16(4.76)	17	42	100 (3.9)
	1⁄4(6.35)	14	37	100 (3.9)
Commercial	1/32(0.79)	60	68	175 (6.9)
	1⁄16(1.59)	52	66	175 (6.9)
	1⁄8(3.18)	35	61	150 (5.9)
	³ ⁄16(4.76)	24	56	100 (3.9)
	1⁄4(6.35)	20	52	100 (3.9)
Electrical insulation	0.004 to 0.007 (0.10 to 0.18), incl			200 (7.9)
	over 0.007 to 0.040 (0.18 to 1.02), incl			250 (9.8)
	over 0.040 to ½ (1.02 to 3.18), incl			175 (6.9)
	1/32(0.80)	60	68	
	1/16(1.59)	52	66	
	1⁄8(3.17)	35	61	
	1⁄4(6.35)	20	52	100 (3.9)
	5⁄16(7.94)	17	47	100 (3.9)
	3⁄8(9.52)	15	43	100 (3.9)
	7∕16(11.11)	14	39	50 (2.0)
	1⁄2(12.7)	13	36	50 (2.0)
	5⁄8(15.88)	11	31	A
	3⁄4(19.05)	10	27	A
	7⁄8(22.22)	8	23	A
	1 (25.4)	8	21	A
	11⁄4(31.8)	8	18	А
	11⁄2(38.1)	8	17	A
	2 (50.8) and over	8	17	A

^A For intermediate thicknesses, the value for the next smaller thickness shall

apply. $$^{B}\xspace$ For intermediate thicknesses, the value for the next larger thickness shall apply.

9. Rod Sizes and Permissible Variations

9.1 Furnish rods in the same nominal sizes as sheets. Cut rods from sheet, the length being limited by the length of the sheet.

TABLE 5 Bursting Strength Requirements for Sheets, min, psi (MPa)

Nominal Thickness, in. (mm)	Bone Grade	Commercial Grade	Electrical Insula- tion Grade
0.005 (0.13)			65 (0.4)
0.007 (0.18)			95 (8.7)
0.010 (0.25)		125 (0.9)	125 (0.9)
0.012 (0.30)		150 (1.0)	150 (1.0)
0.015 (0.38)		185 (1.3)	185 (1.3)
0.020 (0.51)		250 (1.7)	250 (1.7)
0.030 (0.76)	325 (2.2)	375 (2.6)	375 (2.6)
0.045 (1.14)	470 (3.2)	560 (3.9)	560 (3.9)
0.060 (1.52)	550 (3.8)	750 (5.2)	750 (5.2)

TABLE 6 Density Requirements for Sheets, min, g/cm^{3A}

Neminal Thiskness or	Commercial Grade		Electric Insulation Grade	
Diameter, in. (mm)	Uncalen- dered	Calen- dered	Uncalen- dered	Calen- dered
Under 0.010 (0.25)			0.90	1.00
0.010 to 0.015 incl,	1.05	1.10	1.00	1.10
(0.25 + 0.38),				
Over 0.015 to 3/32 incl, (0.38	1.10	1.15	1.10	1.15
to 2.38),				
Over 3/32 to 1/8 incl, (2.38 to	1.15	1.20	1.15	1.20
3.18),				
Over 1/8 to 5/8 incl, (3.18 to		1.20		
15.88),				
Over 5/8to 1 incl, (15.88 to		1.10		
25.4),				
Over 1 to 11/4 incl, (25.4 to		1.05		
31.8),				
Over 11/4 (31.8)		1.01		

^A The minimum density of all forms and thicknesses of bone grade shall be 1.30 g/cm³.

TABLE 7 Tearing Strength Requirements for Sheets, Electric Insulation Grade

Nominal Thickness, in. (mm)	Machine Direction, min, g	Cross Direction, min, g
0.005 (0.13)	75	100
0.007 (0.18)	150	175
0.010 (0.25)	225	275
0.012 (0.30)	275	335
0.015 (0.38)	350	425

TABLE 8	Impact	Strength	Requi	rements	for	Sheets
---------	--------	----------	-------	---------	-----	--------

Grade	Nominal Thickness, in. (mm)	Impact Strength, Izod, Edgewi Notched, min, ft-lb/in. J/m of notch		
		Lengthwise	Crosswise	
Bone	¹ / ₁₆ to ¹ / ₄ (1.59 to 6.35)	1.4 (75)	1.0 (53)	
Commercial	¹ / ₁₆ to ¹ / ₄ (1.59 to 6.35)	1.6 (85)	1.2 (64)	
Electrical insulation	1/16 to 1/8 (1.59 to 3.2)	1.6 (85)	1.2 (64)	

9.2 The maximum permissible variations in diameters of rods are as shown in Table 18.

9.3 The maximum permissible variations in lengths of circular sawed pieces of rods are as shown in Table 19.

10. Tube Sizes and Permissible Variations

10.1 The sizes of tubing are as shown in Table 20 and Table 21.

10.2 The maximum permissible variations in inside and outside diameters of tubes are as shown in Table 22.

TABLE 9 Hardness Requirements for Sheets 1/16 in. (1.6 mm) or More in Thickness

Grade	Rockwell Hardness, min
Bone	R 80
Commercial	R 50

TABLE 10 Tensile Strength Requirements for Round Rods, min, psi (MPa)

Nominal Diameter, in. (mm)	Bone Grade	Commercial Grade
1/8 to 1/2 (3.18 to 12.7), incl	8500 (59)	8000 (55)
Over 1/2 (12.7)		7000 (48)

TABLE 11 Water Absorption Requirements for Round Rods

Grade	Nominal Diameter, in. (mm)	Water Absorption, max, %	
		2 h	24 h
Bone	1/16to 3/16 (1.59 to 4.76), incl	35	75
	over 3/16 to 1/4 (4.76 to 6.35), incl	15	50
Commercial	¹ /16to ³ /16 (1.59 to 4.76), incl	40	80
	over 3/16 to 1/2 (4.76 to 12.7), incl	20	60
	over 1/2 to 1 (12.7 to 25.4), incl	10	30
	over 1	8	25

TABLE 12 Density Requirements for Round Rods

Grade	Nominal Diameter, in. (mm)	Density g/cm ³ , min
Bone	$\frac{1}{160} \frac{3}{32}$ (1.59 to 2.38), incl over $\frac{3}{32}$ (2.38)	1.15 1.30
Commercial	over ³ / ₂₂ to ⁵ / ₈ (2.38 to 15.88), incl over ⁵ / ₈ to 1 (15.88 to 25.4), incl over 1 to 1 ¹ / ₄ (25.4 to 31.8), incl over 1 ¹ / ₄ (31.8)	1.20 1.10 1.05 1.01

TABLE 13 Compressive Strength Requirement for Round Tubes

Grade Nominal Wall Thickness, in. ^{<i>A</i>} (mm)		Axial Compressive Strength, min, psi (MPa)	
Bone and commercial	up to 1/8 (3.18), incl over 1/8 to 5/16 (3.18 to 7.94), incl	11 000 (76) 12 000 (33)	

^A Wall thickness 1/32 in. min; outside diameter 2.0 in. max.

10.3 The maximum permissible variations in length of circular sawed pieces of tubes are as shown in Table 23.

11. Workmanship

11.1 The material shall be uniform in quality and consistent with the properties prescribed in this specification. It shall be free of blisters, and reasonably free of wrinkles, cracks, scratches, and dents.

12. Sampling

12.1 To determine conformance with the requirements of this specification, sample lots in accordance with Inspection Level S-2 of Practice D 3636.

13. Test Methods

13.1 Condition vulcanized fibre and test in accordance with Test Methods D 619.

🖽 D 710 – 97 (2002)

Grade	Nominal Wall Thickness, in. (mm) –	Water Absor	otion, max, %	Dielectric Strength, min,
		2 h	24 h	V/mil (kV/mm)
Bone and commercial	up to 1/16 (1.59)			175 (6.9)
	over 1/16 to 1/8 (1.59 to 3.18), incl			150 (5.9)
	1/32to 1/8 (0.79 to 3.18), incl	50	75	
	over 1/8 to 1/4 (3.18 to 6.35), incl	20	50	100 (3.9)
	over 1/4 to 5/16 (6.35 to 7.94), incl	10	25	100 (3.9)

TABLE 14 Water Absorption and Dielectric Strength Requirements for Round Tubes

TABLE 15 Range of Manufacturers' Sheet Sizes

NOTE 1—Due to variations in the size of manufacturing equipment, there is some variation in the length and width of manufacturers' standard sheet sizes. Consult manufacturers' catalogs for sizes available. The ranges of manufacturers' standard sheet sizes are as follows:

Grade	Width, in. (mm)	Length, in. (mm)
Bone	40 to 54	66 to 86
	(1016 to 1322)	(1676 to 2184)
Commercial	45 to 56	72 to 90
	(1143 to 1422)	(1829 to 2286)
Electrical insulation	46 to 56	80 to 90
	(1168 to 1422)	(2032 to 2286)
Laminated form	48	39 to 120
	(1219)	(991 to 3048)

TABLE 16 Permissible Variations in Widths of Strip Cut from Sheets of All Grades, Plus or Minus, in.^A

Width, in. (mm)	Slit (Ribbon Rolls)	Sheared	Band Sawed	Smooth Sawed
³ /16(4.76) and under	0.010	0.015	0.020	0.006
1/4 to 1/2 (6.35 to 12.7), incl	0.015	0.020	0.030	0.008
%16to 1 (14.29 to 25.4), incl	0.020	0.030	0.045	0.010
11/sto 2 (28.58 to 50.8), incl	0.030	0.040	0.060	0.012
Over 2 to 4 (50.8 to 101.6)	0.040	0.050	0.075	0.014

^A On strip of widths not listed in this table, the permissible variations shall be the same as for the next greater width.

14. Inspection

14.1 The purchaser and supplier shall agree upon the inspection as part of the purchase contract.

🖽 D 710 – 97 (2002)

TABLE 17 Permissible Variations in Thickness of Full Sheets and Sheets Cut in Halves, Thirds, and Quarters of all Grades^A

Nominal Thickness, in. (mm)	Full Sheets, plus or minus, in. (mm)	¹ ⁄ ₂ , ¹ ⁄ ₃ , ¹ ⁄ ₄ Sheets, plus or minus, in. (mm)
0.004 to 0.040 (0.10 to 1.02)	10 %	8 %
0.041 to 0.049 (1.04 to 1.24)	0.004 (0.10)	8 %
0.050 to 0.062 (1.27 to 1.57)	0.005 (0.13)	0.004 (0.10)
0.063 to 0.094 (1.60 to 2.39)	0.007 (0.18)	0.005 (0.13)
0.095 to 0.125 (2.41 to 3.18)	0.010 (0.25)	0.008 (0.20)
0.126 to 0.188 (3.20 to 4.78)	0.025 (0.64)	0.020 (0.50)
0.189 to 0.250 (4.80 to 6.35)	0.030 (0.76)	0.025 (0.64)
over 1/4 to 3/8 (6.35 to 9.5), incl	0.035 (0.89)	
over 3/8 to 1/2 (9.5 to 12.7), incl	0.040 (1.02)	
over 1/2 to 5/8 (12.7 to 15.9), incl	0.045 (1.14)	
over 5/8to 3/4 (15.9 to 19.0), incl	0.055 (1.40)	
over 3/4to 1 (19.0 to 25.4), incl	0.070 (1.78)	
over 1 to 11/4 (25.4 to 31.8), incl	0.090 (2.29)	
over 11/4 to 11/2 (31.8 to 38.1), incl	0.110 (2.79)	
over 11/2 to 13/4 (38.1 to 44.4), incl	0.130 (3.30)	
over 13/4 to 2 (44.4 to 50.8), incl	0.140 (3.56)	
over 2 to 21/4 (50.8 to 57.2), incl	0.160 (4.06)	
over 21/4 to 21/2 (57.2 to 63.5), incl	0.175 (4.44)	
over 21/2 to 23/4 (63.5 to 69.9), incl	0.190 (4.83)	
over 23/4 to 3 (69.9 to 76.2, incl	0.210 (5.33)	
over 3 to 31/4 (76.2 to 82.6), incl	0.225 (5.72)	
over 31/4 to 31/2 (82.6 to 88.9), incl	0.240 (6.10)	
over 31/2 to 33/4 (88.9 to 95.3), incl	0.260 (6.60)	
over 3 ³ / ₄ to 4 (95.3 to 101.6), incl	0.280 (7.11)	

^A On sheets of nominal thickness not listed in this table, the permissible variations shall be the same as for the next greater thickness.

15. Rejection and Rehearing

15.1 Material that fails to meet the requirements of this specification is subject to rejection. When the number of defectives for any test are in excess of the acceptance number for that test as determined by the AQL value agreed upon between the supplier and the user, this shall constitute a basis for rejection.

15.2 Report rejection to the producer or supplier promptly and in writing. In the case of dissatisfaction with the actions

 TABLE 18 Permissible Variations in Diameter of Round Rods of All Grades, Plus or Minus, in.

Nominal Diameter, in. (mm)	Bone Grade	Commercial Grade
¹ /16to ¹ / ₄ (1.59 to 6.35), incl	0.005	0.005
Over 1/4 to 1/2 (6.35 to 12.7), incl	0.006	0.006
Over 1/2 to 1 (12.7 to 25.4), incl		0.006
Over 1 to 2 (25.4 to 50.8), incl		0.010

TABLE 19 Permissible Variations in Length of Rods of All Grades

Nominal Length, in. (mm)	Permissible Variations in Length as Cut, plus or minus, in. (mm)
0 to 3 (76.2), incl	0.015 (0.38)
Over 3 to 6 (76.2 to 152.4), incl	0.020 (0.51)
Over 6 to 12 (152.4 to 304.8), incl	0.030 (0.76)
Over 12 to 24 (304.8 to 609.6), incl	0.035 (0.89)
Over 24 to 48 (609.6 to 1219.2), incl	0.040 (1.02)
Over 48 to 84 (1219.2 to 2133.6), incl	0.062 (1.57)

taken as a result of these tests, the producer or supplier may make a claim for a rehearing.

16. Certification

16.1 When specified in the purchase order or contract, furnish a producer's or supplier's certification to the purchaser that the material was manufactured, sampled, tested, and inspected in accordance with this specification, and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

17. Keywords

17.1 electrical insulation; fish paper; rigid rods; rigid sheets; rigid tubes; vulcanized fibre

∰ D 710 – 97 (2002)

TABLE 20 Standard Steps in Inside and Outside Diameters of Tubes of All Grades

Nominal Inside Diameter, in. (mm)	Diameters Available in Steps of, in. (mm)	Nominal Outside Diameter, in. (mm)	Diameters Available in Steps of, in. (mm)
1/8 to 3/8 (3.18 to 9.52), incl	1/64(0.40)	3/16 to 1/2 (4.76 to 12.7), incl	1/64 (0.40)
13/32to 1 (10.32 to 25.4), incl	1/32(0.79)	17/32to 11/4 (13.49 to 31.75), incl	1/32 (0.79)
11/16(26.99) and over	1⁄16(1.59)	15/16(33.34) and over	1⁄16 (1.59)

TABLE 21 Wall Thickness of Tubes of All Grades, in.^A

Nominal Inside Diameter, in. (mm)	Min	Мах
1/8 (3.18)	0.020	1/8
5/32 (3.97)	0.020	1/8
3/16 (4.76)	0.020	1/8
7/32 (5.56)	0.020	1/8
1/4 (6.35)	0.020	1/4
⁹ / ₃₂ (7.14)	1/32	1/4
5/16 (7.94)	1/32	1/4
¹¹ / ₃₂ (8.73)	1/32	1/4
3⁄8 (9.52)	1/32	1/4
¹³ / ₃₂ (10.32)	1/32	1/4
7⁄16 (11.11)	1/32	1/4
¹⁵ / ₃₂ (11.96)	1/32	1/4
1/2 (12.7)	1/32	1/4
9/16 (14.29)	1/32	1/4
5∕∞ (15.88)	1/32	1/4
¹¹ / ₁₆ (17.46)	1/32	1/4
3⁄4 (19.05)	1/32	9/32
13/16 (20.64)	1/32	9/32
7/8 (22.22)	1/32	9/32
1 (25.4)	1/32	9/32
11⁄8 (28.58)	1/32	9/32
1¼ (31.75)	1/32	9/32
1¾ (34.92)	1⁄16	9/32
11/2 (38.1)	1/16	5⁄16
4 (101.6) and over	1/8	5⁄16

^A For intermediate sizes, values for the next smaller size shall apply.

🕼 D 710 – 97 (2002)

|--|

Nominal Size of Tubing,	Outside Diameter,	Inside Diameter, Wall Thicknesses as Listed, in. (mm)			
Inside Diameter, in. (mm)	All Wall Thicknesses	1⁄16	1⁄8	3⁄16	Over 3/16
1/4 (6.35) and under	0.004 (0.10)	0.004 (0.10)	0.005 (0.13)	0.006 (0.15)	
17/64to 1 (6.75 to 25.4), incl	0.005 (0.13)	0.005 (0.13)	0.006 (0.15)	0.007 (0.18)	0.008 (0.26)
11/16to 2 (26.99 to 50.8), incl	0.008 (0.20)	0.008 (0.20)	0.008 (0.20)	0.010 (0.25)	0.010 (0.25)
21/16to 4 (52.39 to 101.6), incl	0.010 (0.25)	0.010 (0.25)	0.010 (0.25)	0.015 (0.38)	0.015 (0.38)

^A On tubes of nominal diameters not listed in this table, the permissible variations are the same as for the next greater diameter.

TABLE 23 Permissible Variations in Length of Tubes of All Grades as Cut, Plus or Minus, in.

Nominal Length,	Diameter	Diameter, in. (mm)		
in. (mm)	0 to 3	Over 3 to 6		
0 to 3 (76.2), incl	0.015 (0.38)	0.020 (0.51)		
Over 3 to 6 (76.2 to 152.4), incl	0.020 (0.51)	0.025 (0.64)		
Over 6 to 12 (152.4 to 304.8), incl	0.030 (0.76)	0.035 (0.89)		
Over 12 (304.8)	0.035 (0.89)	0.045 (1.14)		

APPENDIX

(Nonmandatory Information)

X1. ENGINEERING DATA

X1.1 The following information and engineering data are considered to be of value to the purchaser of the material covered by this specification to better acquaint him with what is to be expected in operations involving handling and storage of vulcanized fibre.

X1.2 Thermal Expansion:

X1.2.1 The coefficient of thermal expansion per degree Celsius as determined by Test Method D 696, is approximately as follows:

Direction of	Coefficient of		
Measurement	Thermal Expansion		
Machine direction	0.00002		
Cross direction	0.00003		

X1.3 Modulus of Elasticity:

X1.3.1 Typical values of modulus of elasticity in tension for $\frac{1}{4}$ -in. (6.4 mm) vulcanized fibre are as follows:

Direction	Modulus of Elasticity in Tension, psi (MPa)	
Machine direction	1 200 000 (8270) 800 000 (5515)	

X1.3.2 Typical values of modulus of elasticity in flexure for $\frac{1}{4}$ -in. vulcanized fibre are as follows:

Direction	Modulus of Elasticity in Flexure, psi (MPa)	
Machine direction	1 000 000 (6890)	
Cross direction	700 000 (9830)	

X1.4 Dimensional Change with Change in Moisture Content:

X1.4.1 The dimensions of vulcanized fibre increase as the moisture content increases in accordance with certain definite

relationships. The amount of change for each 1 % of change in moisture content is 1 % in thickness, 0.25 % in width, and 0.1 % in length. Although the dimensional change tends to run slightly greater in higher density grades than in lower density grades, the difference is so slight that the figures given above are generally applicable. It should be understood that these values, at best, are approximate.

X1.5 Equilibrium Moisture Content:

X1.5.1 Vulcanized fibre adjusts its moisture content to correspond with the atmospheric humidity to which it is exposed. The moisture content of vulcanized fibre is determined by the procedure given in Test Methods D 619 and is expressed as a percentage of the dry weight of the test specimen employed.

X1.5.2 The approximate amount of moisture which vulcanized fibre will hold at equilibrium under various relative humidity conditions at approximately 23°C is indicated by the curve shown in Fig. X1.1. This curve applies to the various grades of vulcanized fibre in normal use, although the rate of absorption tends to vary, with the lower density grades absorbing moisture faster than the higher density grades.

NOTE X1.1—In the winter season vulcanized fibre is often stored in a heated room after the fibre has reached moisture equilibrium in the cold atmosphere. Unless moisture is added to the storage room, the vulcanized fibre will tend to reach a new lower moisture equilibrium.

X1.6 Recommended Storage Conditions:

X1.6.1 For general uses, vulcanized fibre should be stored where it will maintain its normal moisture content of approximately 5 to 8 %.

X1.6.2 If subjected to extremely damp conditions, it will pick up moisture and tend to warp out of shape and to increase its dimensions slightly.



FIG. X1.1 Typical Curve Showing Equilibrium Moisture Content of Vulcanized Fibre Under Various Humidities at 23°C

X1.6.3 If subjected to extremely dry conditions, such as the low humidity that develops in heated rooms during the winter season, it will tend to dry out. This tends to cause warpage and slight shrinkage in all dimensions as well as some increase in stiffness and hardness.

X1.6.4 Avoid storing fibre under extremely damp or extremely dry conditions. Approximately 50 % relative humidity is recommended.

X1.7 Electrical Characteristics:

X1.7.1 Vulcanized fibre possesses excellent arcextinguishing and nontracking characteristics which make it particularly suitable in many kinds of equipment where these properties are required, for example, arc chutes for small circuit breakers, lightning arrestors, both high and low voltage fuses of many types and expulsion type high voltage cutouts. An increase in moisture content usually improves the arcextinguishing and nontracking characteristics.

X1.7.2 Moisture Content influences the voltage breakdown, dc resistivity and ac permittivity and dissipation factor of hard fibre to an extent that makes it difficult to evaluate these properties in a standardized manner. Under relatively wet conditions, these characteristics will be negatively affected as compared to dry conditions. This characteristic could possibly limit certain applications unless previ-ously approved by testing.

X1.8 Resistance to Heat:

X1.8.1 By experience, vulcanized fibre has been found to have a temperature index of 110 for mechanical grades and115 for electrical grades.

X1.8.2 For optimum performance, it is desirable that the normal moisture content be maintained. A reduction in moisture content from the normal range produces slight shrinkage, warpage, and a decrease in toughness as indicated by the impact test, and produces an increase in such properties as compressive strength, flexural strength, modulus of elasticity, hardness, and tensile strength. Slight deviations in moisture content from the normal do not produce any permanent harmful effects. Vulcanized fibre is superior in heat resistance to cellulose insulation of the unconverted type.

X1.9 Tensile Strength:

X1.9.1 Typical values of tensile strength of sheets are given in Table X1.1.

X1.9.2 Typical tensile strength of round tubes is 12 000 psi for all sizes having wall thickness of $\frac{1}{32}$ in. (1.5 mm) min, and outside diameter of 2 in. (51 mm) max.

X1.10 Compressive Strength:

X1.10.1 Typical values for compressive strength of sheets and round rods are given in Table X1.2.

TABLE X1.1 Typical Values of Tensile Strength of Sheets, psi (MPa)

Thickness, in. (mm)	Bone	Bone Grade		Commercial and Electric Insulation Grades	
	Crosswise	Lengthwise	Crosswise	Lengthwise	
Up to 1/8	8 000 (56)	14 000 (97)	7 500 (52)	13 500 (93)	
Over 1/8 (3.18) to 1/2 (12.7), incl	7 000 (48)	11 000 (76)	7 000 (48)	11 000 (76)	
Over 1/2 (12.7)			6 000 (41)	7 000 (48)	

∰ D 710 – 97 (2002)

TABLE X1.2 Typical Values for Compressive Strength of Sheets and Round Rods, psi (MPa)

Grade	Sheets (Flatwise)	Round Rods (Axial)	
	(all thicknesses)	(all diameters)	
Bone	30 000 (207)	12 000 (83)	
Commercial	25 000 (172)	10 000 (69)	

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).