



## Standard Test Method for Durability of Finish of Zippers to Drycleaning<sup>1</sup>

This standard is issued under the fixed designation D 2058; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the determination of the durability of the enamel or other decorative coating of zippers when subjected to drycleaning.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

D 123 Terminology Relating to Textiles

D 2050 Terminology Relating to Zippers

D 2051 Test Method for Durability of Finish of Zippers to Laundering

D 2052 Test Method for Colorfastness of Zippers to Drycleaning

D 2053 Test Method for Colorfastness of Zippers to Light

D 2054 Test Method for Colorfastness of Zipper Tapes to Crocking

D 2057 Test Method for Colorfastness of Zippers to Laundering

D 2059 Test Method for Resistance of Zippers to Salt Spray (Fog)

D 2060 Test Methods for Measuring Zipper Dimensions

D 2061 Test Methods for Strength Tests for Zippers

D 2062 Test Methods for Operability of Zippers

#### 2.2 AATCC Method:

Method 86 Drycleaning: Durability of Applied Designs and Finishes<sup>3</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 For definitions of zipper terms used in this standard, refer to Terminology D 2050. For definitions of other textile terminology used in this standard refer to Terminology D 123.

### 4. Summary of Test Method

4.1 A specimen is agitated in a solution of solvent and a drycleaning detergent with steel balls to simulate the action that occurs in a drycleaning machine.

### 5. Significance and Use

5.1 Test Method D 2058 is useful for determining the effect of repeated drycleaning on the appearance of the decorative coating of a zipper.

5.2 This test method is considered satisfactory for acceptance testing of commercial shipments because the method has been used extensively in the trade for acceptance testing.

5.2.1 If there are differences of practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is a statistical bias between them, using competent statistical assistance. As a minimum, the test samples should be used that are as homogeneous as possible, that are drawn from the material from which the disparate test results were obtained, and that are randomly assigned in equal numbers to each laboratory for testing. Other materials with established test values may be used for this purpose. The test results from the two laboratories should be compared using a statistical test unpaired data, at a probability level chosen prior to the testing series. If a bias is found, either its cause must be found and corrected, or future test results must be adjusted in consideration of the known bias.

5.3 The method(s) in the standard along with those in Test Methods D 2051, D 2052, D 2053, D 2054, D 2057, D 2059, D 2060, D 2061, and D 2062 are a collection of proven test methods. They can be used as aids in the evaluation of zippers without the need for a thorough knowledge of zippers. The enumerated test methods do not provide for the evaluation of all zipper properties. Besides those properties measured by means of the enumerated test methods there are other properties that may be important for the satisfactory performance of a zipper. Test methods for measuring those properties have not been published either because no practical methods have yet

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D13 on Textiles, and is the direct responsibility of Subcommittee D13.54 on Subassemblies. The method was developed in cooperation with the Slide Fastener Assn. Inc.

Current edition approved Dec. 1, 2003. Published December 2003. Originally approved in 1961. Last previous edition approved in 1997 as D 2058 – 87 (1997).

<sup>2</sup> For referenced ASTM standards, visit the ASTM web site, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM web site.

<sup>3</sup> Technical Manual of the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.

been developed or because a valid evaluation of the information resulting from existing unpublished methods requires an intimate and thorough knowledge of zippers.

## 6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of individual containers from each shipping carton as directed in an applicable material specification or other agreement between the purchaser and the supplier. Consider individual containers from each shipping carton to be the primary sampling units.

NOTE 1—An adequate specification or other agreement between the purchaser and supplier requires taking into account the variability between shipping cartons and between zippers in a container to provide a sampling plan with a meaningful producer's risk, consumer's risk, acceptable quality level, and limiting quality level.

6.2 *Laboratory Sample and Test Specimens*—As a laboratory sample for acceptance testing, take at random two zippers from each container in the lot sample. Consider the zippers as both the laboratory samples and the test specimens.

## 7. Test Specimen

7.1 The test specimen shall consist either of a completely assembled zipper or a length of chain. In either case, the length shall not be greater than 254 mm (10 in.). In the case of a completely assembled zipper that is longer than 254 mm, the specimen may be made up by cutting out and removing the central portion of the chain, and then securely attaching the cut ends together, using suitable noncorrosive materials such as sewing thread or stainless steel staples. If it is desired to test the entire length of a long zipper, it should be cut into parts 254 mm or less in length and those parts tested separately.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*

## 8. Conditioning

8.1 No special environmental conditions are required.

## 9. Procedure

9.1 Test each specimen as directed in AATCC Test Method 86, except air dry only rather than hot press the specimen.

## 10. Interpretation of Results

10.1 Interpret the results of the tests on specimens by visually examining the chain and components for exposed base metal and compare observations to samples illustrating an acceptable degree of coating loss as agreed upon between the purchaser and the supplier.

## 11. Report

11.1 State that the specimens were tested as directed in ASTM Test Method D 2058. Describe the material or product sampled, and the method of sampling used.

11.2 Report the following information:

11.2.1 Number of specimens tested, and

11.2.2 Number of specimens equal to or not equal to the agreed upon standard.

## 12. Precision and Bias

12.1 No justifiable statistical statement can be made on either the precision or the bias of the procedures in ASTM Test Method D 2058 for testing coating resistance to abrasion in drycleaning, since the method can be used only to secure information concerning the conformance of a specimen with previously agreed upon standards.

## 13. Keywords

13.1 drycleaning; durability; zipper