



Standard Test Method for Softening Point of Pitch (Cube-in-Air Method)¹

This standard is issued under the fixed designation D 2319; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the softening point above 176°F (80°C) of pitch. Test Method D 3104 gives comparable results.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D 61 Test Method for Softening Point of Pitches (Cube-in-Water Method)

D 3104 Test Method for Softening Point of Pitches (Mettler Softening Point Method)

D 4296 Practice for Sampling Pitch

E 1 Specification for ASTM Thermometers

3. Summary of Test Method

3.1 Two cubes of pitch, supported on wire hooks, are heated in a standardized air oven at a linear rate. The softening point is the mean of the temperatures at which the cubes sag downwards a distance of 60 mm (2.4 in.).

4. Significance and Use

4.1 Pitch does not go through a solid-liquid phase change when heated and therefore does not have a true melting point. As the temperature is raised, pitch softens and becomes less viscous. The softening point is arbitrarily defined and must be determined by a closely controlled method that must be carefully followed if test results are to be reproducible.

4.2 This test method is useful in determining the consistency of pitch as one element in establishing the uniformity of shipments and sources of supply.

5. Apparatus³

5.1 *Air Oven*—The oven shall be cylindrical, 150 mm (6 in.) in inside diameter by 155 mm (6.2 in.) in height. It shall have two 75 mm (3-in.) diameter windows of mica, centered vertically on opposite sides, and shall be fitted with a cover having a central opening 25 mm (1 in.) in diameter to hold a thermometer, and a concentric ring suspended below to support the hooks with attached specimens. The ring shall be made of 6 mm (1/4-in.) brass, shall be 54 mm (2 1/8 in.) in outside diameter, and shall be centrally suspended 30 mm (1.2 in.) below the cover. The cover shall have two 3 mm (0.12-in.) holes on a diagonal 50 mm (2 in.) from the center. On the bottom of the oven, an inner pan 140 mm (5.6 in.) in diameter shall rest on three brass legs 5 mm (0.2 in.) in height fastened to the bottom of the pan to provide an air space between the pan and the bottom of the oven. The side wall, cover, and pan shall be made of 0.7 mm (0.028 in.) thick or 22-gage (BWG) copper sheet, and the bottom of 0.8 mm (0.032 in.) thick or 21-gage copper.

5.2 *Tripod for Use with Gas Burner*—The tripod ring shall be approximately 125 mm (5 in.) in inside diameter so that the oven is supported only on its outer edges. It shall be 200 mm (8 in.) in height.

5.3 Shield for Oven:

5.3.1 *For Use with Electric Heater*—The shield shall be cylindrical, 216 mm or (8.64 in.) in inside diameter by 181 mm or (7 1/4 in.) in height. It shall have two 76 mm or (3-in.) diameter mica windows on opposite sides, positioned to coincide with the windows of the oven when both are placed on the electric heater. It shall be made of 0.7 mm (0.028 in.) thick or 22-gage sheet metal, painted inside and out with aluminum paint.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.05 on Properties of Fuels, Petroleum Coke and Carbon Material.

Current edition approved Nov. 1, 2003. Published November 2003. Originally approved in 1964. Last previous edition approved in 1998 as D 2319-98.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The sole source of supply of the softening point apparatus items, obtainable as a unit on special order, known to the committee at this time is Humboldt Manufacturing Co., 7302 W. Agatite Ave., Chicago, IL 60656. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend. All other apparatus items described may be obtained from any regular laboratory equipment supply house.

5.3.2 For Use with Gas Burner—The shield shall be identical with that described in 5.3.1 except that it shall be 375 mm (15 in.) in height and the windows shall coincide when the shield is standing on the bench and the oven on the tripod described in 5.2. A door 115 by 115 mm (4½ by 4½ in.) shall be provided at the bottom to give access to the burner.

5.4 Mold—A mold suitable for forming two 12.7 mm (½-in.) cubes of pitch, having cylindrical core pins 12 gage (2.05 to 2.07 mm) in diameter located in the base plate of the assembly to produce accurately centered suspension holes in the cubes. See Fig. 1 of Test Method D 61 for details.

5.5 Hooks—Two L-shaped hooks made of 2.06 mm or 12-gage copper wire. The foot of the hook shall be 25 mm (1 in.) in length and at a right angle to the upright portion for insertion into the central hole of the pitch cube. The upright portion shall have a partial loop at the top to fit over the support ring, and shall be of the proper length, approximately 50 mm (2 in.), to position the foot on an imaginary line running horizontally through the center of the windows.

5.6 Thermometer—ASTM High-Softening Point Thermometer, having a range from 30 to 200°C (80 to 400°F), and conforming to the requirements for Thermometer 16C as described in Specification E 1.

5.7 Heat Source:

5.7.1 Electric Heater—A hot plate provided with a variable transformer or other device for regulating the temperature of the heating element. It should be shielded from drafts on three sides.

5.7.2 Gas Burner, bunsen-type, with a chimney and a sensitive valve for regulating the size of the flame.

6. Bulk Sampling

6.1 Samples from shipments shall be taken in accordance with Practice D 4296 and shall be free of foreign substances. Thoroughly mix the sample before removing a representative portion for the determination or for dehydration.

7. Dehydration

7.1 If the bulk sample contains free water, air-dry a representative portion in a forced draft oven at 50°C.

8. Test Specimens

8.1 To melt a solid pitch sample, add the material to a container having a height equal to or exceeding its width, and a volume of not less than 50 mL, until it is about half full. Place the container on a hot plate, or in an oven or bath. Do not use an open flame for melting pitch. After melting is complete, stir thoroughly but gently with the thermometer or glass rod, avoiding the incorporation of air bubbles. The maximum temperature shall not exceed the expected softening point by more than 50°C (90°F). Any foam that may form must be skimmed off the surface.

8.2 Coat the inner surfaces and core pins of the mold lightly with silicone oil or silicone grease. Pour molten pitch into the cavities of the mold with the lip of the container close to the surface to minimize entrainment of air bubbles. Underpouring past the blade of a spatula is helpful in this respect. Even small bubbles markedly effect the weight of the cube and the

observed softening point. Use an excess of pitch to allow for shrinkage on cooling. Cool in the mold until firm, and remove the surplus by drawing the heated blade of a putty-knife or spatula across the surface of the mold so that the cubes are pressed into the cavities. Open the mold and remove the cubes carefully. Inspect each specimen for possible cracks or bubbles and reject any which are imperfect. To reduce the risk of cracking, the mold may be heated to a temperature 50°C (90°F) below the expected softening point before the specimens are poured.

8.3 Place two cubes of pitch on hooks, as shown in Fig. 1 of Test Method D 61, warming the hooks slightly if necessary. The foot of the hook passes through the center of two opposite faces, while the other four shall be at an angle of 45° to the horizontal. The shaft of the hook shall be 3 to 5 mm (0.1 to 0.2 in.) from the specimen.

9. Preparation of Apparatus

9.1 Assemble the apparatus in an area free of drafts.

9.2 Ensure that the oven, cover, and pan are clean, bright, and free of dents, since tarnished or dirty apparatus may change the apparent softening point. After each determination, carefully clean the hooks with a solvent for pitch. Avoid scraping or other mechanical methods that may alter the diameter of the wire, which shall be checked frequently for conformance with the specified 2.05 to 2.07 mm (0.082 in.) diameter.

9.3 Set the pan on its legs on the bottom of the oven. Center it so that the space for air circulation is approximately equal all around the circumference. Place a single 110 mm (4.4 in) filter paper on the pan.

9.4 Specimens and oven are normally at room temperature. For harder pitches, the oven may be preheated to a temperature not higher than 60°C (108°F) below the expected softening point.

10. Procedure

10.1 Suspend the hooks with the test specimens in place from the supporting ring on the oven cover with the tips of the hooks pointing toward each other from the left and right sides of the thermometer as viewed through the windows. The feet of the hooks shall lie along an imaginary horizontal line through the center of the windows.

10.2 Insert the thermometer through a cork in the central hole in the cover so that the bottom of the bulb is level with the bottom edges of the cubes, and the ends of the feet of the hooks are close to, but do not touch, the bulb.

10.3 Center the oven on the heat source and place the shield around it so that the two are concentric.

10.4 Preheat the oven if necessary and, when equilibrium is established, adjust the heating rate so that the temperature rises at 5°C/min (10°F/min). The maximum permissible variation from this rate shall be ±1.0°C/min (±2°F/min) for the final 50°C (90°F) below the softening point.

10.5 Maintain a written record of the temperature to 0.25°C (0.5°F) for each minute over the last 50°C (90°F). Average these readings algebraically. The average shall not deviate more than ±0.5°C (±1°F) from the 5°C/min (10°F/min) over this interval. Reject any test in which the rate for any minute in

this interval is outside the range from 4 to 6°C (7 to 11°F), or the average is outside the range from 4.5 to 5.5°C (8 to 10°F).

10.6 The softening point is the average of the thermometer readings (with no correction for emergent stem) when the two cubes touch the pan. Estimate the readings to 0.25°C (0.5°F). If the individual values differ by more than 1.5°C (2.7°F), reject the result and repeat the test.

11. Report

11.1 Report the average as the softening point to the nearest 1°F. If the result is required in degrees Celsius, report to the nearest 0.5°C.

12. Precision and Bias

12.1 The following criteria shall be used to judge the acceptability of results (95 % confidence level) for softening point (cube-in-air):

12.1.1 *Repeatability*—Duplicate results by the same operator shall not be considered suspect unless they differ by more than 1.0°C (2°F).

12.1.2 *Reproducibility*—The values reported by each of two laboratories, representing the arithmetic average of duplicate determinations, shall not be considered suspect unless they differ by more than 7.2°F (4.0°C).

12.1.3 *Bias*—This procedure has no bias because the value of softening point is defined in terms of this test method.

13. Keywords

13.1 cube-in-air; pitch; softening point

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).