



Standard Performance Specification for Women's and Girls' Knitted Blouse and Dress Fabrics¹

This standard is issued under the fixed designation D 4235; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers knitted fabrics comprised of any textile fiber or mixture of fibers, used in women's and girls' blouses and dresses women's and girls' knitted blouse and dress fabrics composed of any fiber or mixture of textile fibers.

1.2 These requirements apply to the length and width directions for those properties where each fabric direction is pertinent.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 123 Terminology Relating to Textiles²
- D 2594 Test Methods for Stretch Properties of Knitted Fabrics Having Low Power²
- D 2724 Test Methods for Bonded, Fused, and Laminated Apparel Fabrics²
- D 2905 Practice for Statements on Number of Specimens for Textiles²
- D 3786 Test Method for Hydraulic Bursting Strength of Knitted Goods and Nonwoven Fabrics: Diaphragm Bursting Strength Tester Method³
- D 3787 Test Method for Bursting Strength of Knitted Goods: Constant-Rate-of-Traverse (CRT) Ball Burst Test³
- 2.2 AATCC Methods:⁴
 - 8 Colorfastness to Crocking: AATCC Crockmeter Method
 - 15 Colorfastness to Perspiration
 - 16 Colorfastness to Light
 - 23 Colorfastness to Burnt Gas Fumes
 - 61 Colorfastness to Washing, Domestic, and Laundering, Commercial: Accelerated
 - 116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method

- 124 Appearance of Durable Press Fabrics after Repeated Home Launderings
- 132 Colorfastness to Drycleaning
- 135 Dimensional Changes in Automatic Home Laundering of Durable Press Woven or Knit Fabrics
- 172 Colorfastness to Non-chlorine Bleach in Home Laundering
- 188 Colorfastness to Chlorine Bleach in Home Laundering Evaluation Procedure 1 Gray Scale for Color Change Evaluation Procedure 2 Gray Scale for Staining Evaluation Procedure 3 AATCC Chromatic Transference Scale
- 2.3 Federal Standard:⁵
 - 16 CFR, Chapter II-Consumer Product Safety Commission Subchapter D-Flammable Fabrics Act Regulations.
- 2.4 Military Standard:⁶
 - MIL-STD-105D Sampling Procedures and Tables for Inspection by Attributes

NOTE 1—Reference to test methods in this standard give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

3. Terminology

3.1 Definition:

3.1.1 *sheer, n*—a fabric that is transparently thin or diaphanous.

3.1.1.1 *Discussion*—There is no clear distinction between sheer fabrics and nonsheer fabrics. The purchaser and the seller should agree in advance into which category a fabric should be classified.

3.2 For definitions of other textile terms used in this specification, refer to the individual ASTM and AATCC test methods and to Terminology D 123.

4. Specification Requirements

4.1 The properties of knitted fabrics for women's and girls' blouses and dresses shall conform to the specification requirements in Table 1.

5. Significance and Use

5.1 Upon mutual agreement between the purchaser and the

¹ This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel. Current edition approved May 10, 2001. Published July 2001. Originally published as D 4235 – 83. Last previous edition D 4253 – 95.

² *Annual Book of ASTM Standards*, Vol 07.01.

³ Discontinued; see 1997 *Annual Book of ASTM Standards*, Vol 07.02.

⁴ Available from The American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, N.C. 27709.

⁵ Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

</

TABLE 1 Specification Requirement^A

Characteristic	Requirements		Section
	Sheer Fabrics	NonSheer Fabrics	
<i>Bursting Strength</i> (ball burst) ^B	20 lbf (89 N), min	30 lbf (133 N), min	7.1
<i>Dimensional Change:</i>			
Laundering (see 7.2.1.2)	3 % max	3 % max	7.2.1
Drycleaning	3 % max	3 % max	7.2.2
<i>Colorfastness:</i>			
Burnt gas fumes, 2 cycles			7.3.1
Shade Change, original	Class 4 ^C , min	Class 4 ^C , min	
Shade change, after one laundering	Class 4 ^C , min	Class 4 ^C , min	
or			
one drycleaning			
Laundering:			7.3.2
Shade Change	Class 4 ^C , min	Class 4 ^C , min	
Staining	Class 3 ^D , min	Class 3 ^D , min	
Drycleaning:			7.3.3
Shade Change	Class 4 ^C , min	Class 4 ^C , min	
Crocking:			7.3.4
Dry	Class 4 ^E , min	Class 4 ^E , min	
Wet	Class 3 ^E , min	Class 3 ^E , min	
Perspiration:			7.3.5
Shade Change	Class 4 ^C , min	Class 4 ^C , min	
Staining	Class 3 ^D , min	Class 3 ^D , min	
Light (20 AATCC FU) (xenon-arc)	Step 4 ^C , min	Step 4 ^C , min	7.3.6
Chlorine Bleach	Class 4 ^C , min	Class 4 ^C , min	7.3.7
Non-chlorine Bleach	Class 4 ^C , min	Class 4 ^C , min	7.3.8
<i>Fabric Appearance</i> (see 7.4.1.1)	DP 3.5, min	DP 3.5, min	7.4
<i>Flammability</i>	pass	pass	7.5

^A Class in colorfastness is based on a numerical scale of 5 for negligible color change or color transfer to 1 for very severe color change or color transfer.

^B There is more than one standard method that can be used to measure bursting strength and lightfastness. These methods cannot be used interchangeably since there may be no overall correlation between them (see 3.1.1 and Note 2, Note 3, Note 4, and Note 5).

^C AATCC Gray Scale for Color Change.

^D AATCC Gray Scale for Staining.

^E AATCC Chromatic Transference Scale.

seller, fabrics intended for this end use should meet all of the requirements listed in Table 1 of this specification.

5.2 It is recognized that for purposes of fashion or aesthetics, the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in Table 1. Therefore, one or more of the requirements listed in Table 1 may be modified by mutual agreement between the purchaser and the seller.

5.2.1 In such cases, any references to the specification shall specify that: "This fabric meets ASTM Specification D 4235 except for the following characteristic(s)."

5.3 Where no prepurchase agreement has been reached between the purchaser and the seller, and in case of controversy, the requirements listed in Table 1 are intended to be used as a guide only. As noted in 5.2, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The uses and significance of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable specification or other agreement between the purchaser and the supplier, such as an agreement

the laundered fabric and the percent shrinkage due to laundering does not exceed 3 % shrinkage, then the fabric meets the specification requirement in Table 1.

7.2.2 Drycleaning—Determine the maximum dimensional change after three drycleanings, or as agreed between the purchaser and the seller, as directed in Sections 10.1.3 through 10.1.4.5 of Test Methods D 2724.

NOTE 4—Launderable fabrics are expected to be drycleanable except where all or part of the fabric is not drycleanable and is so labeled. For example, the fabric could contain a functional finish soluble in the solvent, or the fiber could be degraded by the solvent, which would be the case with poly (vinyl chloride) fiber. “Drycleanable” goods are to be dry-cleaned only.

7.3 Colorfastness:

7.3.1 Burnt Gas Fumes—Determine the colorfastness to burnt gas fumes on the original fabric and after one laundering or one drycleaning as directed in AATCC Method 23 after 2 cycles.

NOTE 5—Washing conditions shall be the same as those used in 7.2.1.1. Drycleaning conditions shall be the same as those used in 7.2.2.

7.3.2 Laundering—Determine the colorfastness to laundering as directed in the applicable procedure of AATCC Method 61. The test conditions shall be as specified by the seller (Note 4).

7.3.3 Drycleaning—Determine colorfastness to drycleaning as directed in AATCC Method 132 (Note 4).

7.3.4 Crocking—Determine colorfastness to dry and wet crocking as directed in AATCC Method 8 for solid shades and AATCC Method 116 for prints or as agreed between the purchaser and the seller.

7.3.5 Perspiration—Determine colorfastness to perspiration as directed in AATCC Method 15.

7.3.6 Light—Determine colorfastness to light as directed in AATCC Method 16.

NOTE 6—There are distinct differences in spectral distribution between the various types of machines listed in AATCC Method 16, with no overall correlations between them. Consequently, these machines cannot be used interchangeably. In case of controversy, results obtained with the Water Cooled Xenon Arc machine listed in Option E shall prevail.

7.3.7 Colorfastness to Chlorine Bleach—Determine colorfastness to light as directed in AATCC Test Method 16.

7.3.8 Colorfastness to Non-chlorine Bleach—Determine colorfastness to light as directed in AATCC Test Method 16.

7.4 Fabric Appearance—Determine the fabric appearance as directed in AATCC Method 124 after laundering using the wash-and-wear cycle or the normal cycle as agreed between the purchaser and the seller as specified in 7.2.1.1 for washable fabrics or after drycleaning as specified in 7.2.2 for drycleanable fabrics (see Note 3).

7.4.1 For fabrics not intended for use in durable press garments, determine the fabric smoothness after pressing as specified in 10.2.5 of Test Methods D 2724.

7.4.1.1 The fabric smoothness (DP) (durable press) rating of such fabrics, and the DP rating of drycleaned fabrics, shall have decreased no more than ½ rating from that of the fabric before it is laundered or drycleaned.

7.5 Flammability—The flammability requirements shall be as agreed between the purchaser and the seller, provided they meet or exceed those of Part 1610 of the Flammable Fabrics Act Regulations.

8. Keywords

8.1 blouse; dress

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).