Standard Test Method for the Determination of the Dip Tube Retention of a Mechanical Pump Dispenser¹

This standard is issued under the fixed designation D 4334; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the force necessary to separate the dip tube from the body of a mechanical pump dispenser.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:

D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing²

3. Significance and Use

3.1 This test method may be used to establish performance specifications.

3.2 This test method may be used as a quality control assessment.

4. Apparatus

4.1 *Test Stand*—The test apparatus shall be capable of applying a smoothly increasing load to the test specimen until the dip tube is separated from the body of the mechanical pump dispenser.

Note 1—The condition of 4.1 is fulfilled by most motor driven tensile strength testers with a constant rate of elongation.

NOTE 2—The test stand should be equipped with a maximum force indicator.

4.2 Clamps:

4.2.1 *Fixture*, to secure the upper part of the mechanical pump dispenser. The fixture shall secure the dispenser in such a way that there is no slippage between it and the test specimen.

4.2.2 *Clamp*, to secure the dip tube. The clamp shall hold the dip tube in such a way that there is no slippage between the

² Annual Book of ASTM Standards, Vol 08.01.

dip tube and the clamp.

4.2.3 Arrange the fixturing so that the tube is maintained in a position parallel to, and within the colinear plane of, the applied force.

4.3 Scale, graduated in either millimetres or inches.

5. Sampling

5.1 Select an appropriate number of dry, unused pump dispensers at random for precision and accuracy desired. Use of 10 test specimens is recommended, but a minimum of three is acceptable.

6. Conditioning

6.1 If possible, condition the test specimens at $23 \pm 3^{\circ}$ C (73 $\pm 5.4^{\circ}$ F) for not less than 4 h. If the test specimens are not conditioned at the recommended temperature, this should be noted in the test report (see 8.1).

NOTE 3—It is suggested that newly-made samples be allowed to sit for a minimum of 24 h after assembly before retention testing begins.

7. Procedure

7.1 Attach fixtures and clamp to the test standard in accordance with the manufacturer's instructions and in a manner consistent with the pump's geometry.

7.2 Insert the dip tube approximately 12 to 18 mm into the clamp and tighten to prevent slippage.

7.3 Adjust the test stand so that there is 25 mm of exposed dip tube length.

NOTE 4-At this time, there should be a zero reading on the force gage.

7.4 Operate the test stand at 250 mm (10 in.)/min until the dip tube has separated either from the pump dispenser, broken, slipped from the jaws, or reached the limit of cross-head travel. If the recommended cross-head speed is not used, record cross-head speed (see 8.1).

7.5 Record the maximum force reading, N (lb).

7.6 Record the mode of failure for each test specimen tested.

8. Report

8.1 The report shall include the following:

8.1.1 Complete identification of the pump dispenser used including type, source, and manufacturer's code and date of manufacture, if known,

8.1.2 Number of specimens tested,

¹ This test method is under the jurisdiction of ASTM Committee D10 on Packaging, and is the direct responsibility of Subcommittee D10.33 on Mechanical Dispensers.

Current edition approved Oct. 10, 1999. Published December 1999. Originally published as D 4334 – 84. Discontinued 1991. Reinstated 1999.

Copyright © ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States.

8.1.3 Number of dip tubes that were separated from the pump dispensers,

8.1.4 Mean, minimum, maximum, and standard deviation of forces required to separate the dip tubes from pump dispensers, and

8.1.5 Mode of failure for those pump dispensers that did not separate.

9. Precision and Bias

9.1 *Precision*—The precision of Test Method D 4334 is highly dependent on the particular pump dip tube size, dip tube material, and pump style tested. One laboratory has investigated one particular fine mist pump style using a capillary-style dip tube with 50 replicate tests, yielding an average of 3.62 lbf with a range of 4.2 to 3.2 lbf and a standard deviation of 0.34 lbf. Other pumps will have other averages of retention and will have more or less variability between replicate tests. Users of this test method are encouraged to reference historical files of previous tests of similar pumps for an estimate of within laboratory repeatability. Because of this strong product and pump style dependency, further investigation of repeatability and reproducibility is not practicable.

9.2 *Bias*—Test Method D 4334 has no bias because an accepted reference or referee value is not available.

10. Keywords

10.1 dip tube; mechanical pump dispenser; retention

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).